



**NIP** **series** **NAPLES**  
Glazed Porcelain  
UNI EN14411  
Annexe G Group B1a

EPD 




# NP Series


Glazed Porcelain

# NAPLES


## COLOURS



NP-100 White





NP-101 Grey



NP-102 Sable



NP-103 Multi



Slip Resistance		
	R10	+36
	C	



NP-100 White 60x120cm / NP-100 White Hexagon 25.8x29cm



NP-101 Grey 60x120cm / NP-101 Grey Hexagon 25.8x29cm



NP-103 Multi - 60x120cm












NP-102 Sable - 60x120cm



NP-102 Sable - 60x60cm

## TECHNICAL FEATURES

		Norm Standards	Test Results
	Product Classification	UNI EN 14411	Annexe G Group B1a
	Dimensional and surface quality	UNI EN ISO 10545-2	Complies with Standards
	Water absorption	UNE-EN-ISO 10545-3	< 0,5%
	Modulus of Rupture	UNI EN ISO 10545-4	1600-2400 N
	Resistance to Deep abrasion	UNE-EN-ISO 10545-6	<130mm <sup>3</sup>
	Chemical Resistance	UNI EN ISO 10545-13	Ammonium chloride 100 G/L      A Sodium Hypochlorite 20 MG/L      A Hydrochloric Acid 3%      Complies with standards Citric Acid 100 G/L      Complies with standards Potassium Hydroxyde 30 G/L      Complies with standards
	Linear thermal expansion	UNI EN ISO 10545-8	<7,0 x 10 <sup>-6</sup> °C <sup>-1</sup>
	Stain resistance	UNI EN ISO 10545-14	Class 5
	Slip Resistance	DIN 51130 DIN 51097 PTV Pendulum Test Value (Wet)	R10 C +36



# Waxman Ceramics Architectural Tiles

---

**Head Office**                      **01422 377123**

Grove Mills  
Elland  
West Yorkshire  
HX5 9DZ  
England

Email            [info@waxmanarchitectural.co.uk](mailto:info@waxmanarchitectural.co.uk)  
Web              [www.waxmanarchitectural.co.uk](http://www.waxmanarchitectural.co.uk)

**Waxman Ceramics Architectural Tiles is a division of Waxman Ceramics Ltd - Part of the Waxman Group**

The information contained within this document is, to the best of our knowledge, accurate at the time of production. We reserve the right to modify this document at any time. Whilst every attempt has been made to accurately reproduce colours and textures, images used within this document are only intended as a guide. Please refer to actual product samples before specifying or ordering.